



## #8000 100% SILICONE ROOF COATING HIGH SOLIDS

CAUTION: Avoid prolonged contact with skin or fumes. If irritation occurs seek medical attention. Keep out of reach of children. Read SDS prior to use. For professional use only. Emergency phone number 1-800-424-9300.

### #8000 SPECIFICATION

ASTM D 6694

#### PRODUCT DESCRIPTION

100% silicone based Lucas #8000 is a single part roof coating that creates a barrier that is resistant to natural weathering, is durable, breathable, watertight and weatherproof. Lucas #8000 can be applied over spray applied polyurethane foam, EPDM, PVC, aged acrylic coatings, concrete, asphalt BUR, granulated modified bitumen, and metal roofs. Lucas #8000 has excellent primerless adhesion to many surfaces when tested in accordance with ASTM D 6694.

#### APPLICATION

Surface to be coated must be dry and free of dirt or corrosion particles. Clean with Lucas #115 Universal Wash. EPDM roofs in particular require aggressive power washing and may need to be cleaned twice to remove all surface contamination. Thoroughly rinse the roof after cleaning to remove all detergent. Primerless application is allowed on some substrates, refer to current Lucas Guide Specification for your project. Adhesion test results meeting the requirements of ASTM D 6694 are required for primerless applications. Discoloration of #8000 coating is expected when applied without primer to asphalt surfaces. Asphalt BUR, granulated modified bitumen, and smooth modified bitumen roofs may require Lucas #1015 Resin Primer or #4015 2 Part Epoxy Primer for increased adhesion and/or asphalt bleed through resistance. #8000 is not recommended on aluminum coated roofs. On aged single-ply roofs, #4015 may also be used to increase long term adhesion in areas that retain water. #8000 may be applied to aged PVC with #4015 or #1015 Primer. #8000 may be applied to TPO roofs with Lucas #8015 TPO Primer. On metal substrates where rust is present, after removing all loose material, Lucas #1019 should be applied to the rusty area prior to application of #8000 or #8500. All penetrations, drains, flashings, ponding water areas, terminations, curbs, etc., should be sealed with Lucas #8500 and/or reinforcement as stated in our Lucas Guide Specification. Roof temperature should be above freezing during application. Use #8000 as it comes from the container, no thinning is necessary and mechanically mix prior to use. Apply uniform coat of #8000 at a rate of 1.5 gallon per 100 sq. ft., coverage rates may vary, refer to the current Lucas Guide Specification for your project. A second coat may be necessary, apply the second coat in a multi-directional fashion within 48 hours of application of the first coat for best results.

Light traffic deck systems and non-slip safety walkways may be constructed by using Lucas #402 EPDM granules, available in Gray and Safety Yellow. Review the #402 Product Data Sheet for installation instructions.

This product cures through absorption of moisture from both the substrate and the air. Avoid entraining air when mixing. Cure time will be faster in humid conditions and on substrates that hold moisture such as concrete. Open and partially full containers will skin over quickly. If this occurs, remove the skin and continue using the remaining product.

The preceding directions are basic guidelines only. Please read and understand the complete Lucas Guide Specification for this product for the intended application. The Guide Specification is available from [techsupport@rmlucas.com](mailto:techsupport@rmlucas.com)  
 Clean up: Clean up with Lucas #901.

Shelf Life: Two years from the date of manufacture.

|                        |              |            |
|------------------------|--------------|------------|
| Viscosity              | ASTM D 2196  | 30,000 cps |
| Solids by Weight       | ASTM D 1644* | 98%        |
| Solids by Volume       | ASTM D 2697* | 97%        |
| Weight Per Gallon      | ASTM D 1147  | 11.5 lbs.  |
| Wet Film Per Gallon    | ASTM D 4414  | 16 mils    |
| Dry Film Per Gallon    | SSPC-PA 2    | 15.5 mils  |
| Tensile Strength       | ASTM D 2370  | 478 psi    |
| Elongation             | ASTM D 2370  | 235 %      |
| Tear Strength          | ASTM D 624   | 29 lbf/in  |
| Permeance              | ASTM E 96    | 8.7 perms  |
| Reflectivity – Initial | ASTM C 1549  | .84        |
| Reflectivity – Aged    | ASTM D 1549  | .71        |
| Emissivity             | ASTM C 1371  | .91        |
| SRI                    | LEED         | 106        |
| LRV - White            | ASTM C609    | .92        |
| LRV - Gray             | ASTM C609    | .47        |
| LRV - Tan              | ASTM C609    | .40        |
| Flash Point            | ASTM D 56    | NA         |
| VOC                    | EPA 24       | < 25 g/l   |

Typical physical properties +/- 5%

Container Sizes: 1, 5, 55 gallon

Colors: White, Black, Gray, Tan



TO THE EXTENT ALLOWED BY LOCAL LAW, EXCEPT AS SET FORTH BELOW, SELLER MAKES NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE WITH RESPECT TO THE GOODS HEREIN SOLD. THERE ARE NO OTHER WARRANTIES OF ANY KIND EXPRESS OR IMPLIED BEYOND THE TERMS SET FORTH ON THE FACE HEREOF. NO EMPLOYEE OR AGENT OF SELLER IS AUTHORIZED TO ALTER THE TERMS HEREOF.

Seller warrants that this product shall be free of any defect in material or workmanship under normal use for a period of ONE YEAR from the date of purchase. This warranty does not extend to any defect or failure caused by misuse and/or incorrect application. LIMITATION OF LIABILITY: In the event of a defect or failure falling under this warranty, Buyers sole remedy shall be refund of the purchase price or replacement of the defective material, at Seller's option. Under no circumstances shall Seller be liable for any losses or damages caused by this product, whether direct, indirect, special, incidental or consequential damages, whether based on contract, tort (including negligence) or any other legal theory.

NOTE: Some or all of the foregoing may not apply or may be invalid under the laws applicable to Buyer's purchase or claim. Consult local law to determine the applicability of any of the foregoing in the event of any defect or failure of this product.